



DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

"We Test Per Your Request"

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

January 27, 2022

Mr. Shawn Lee
DONGWON INDUSTRY USA LLC
80 Industrial Road
Suite D
Lodi, NJ 07644

Reference: Laboratory Test Report
Lab Identification No. 48816-12

Dear Mr. Lee:

One (1) fabric sample, identified as **30DN 3% OPENNESS**, was received and tested in accordance with the California Administrative Code Title 19--Public Safety, Section 1237.1 Flame Resistance, Small Scale Test. The results are as follows:

Test Results

<u>Specimen Number</u>	<u>After Flame (sec)</u>		<u>Char Length (in)</u>	
	<u>Length</u>	<u>Width</u>	<u>Length</u>	<u>Width</u>
1	0.0	0.0	4.3	4.7
2	0.0	0.0	4.8	4.2
3	0.0	0.0	4.1	4.6
4	0.0	0.0	4.2	4.4
5	<u>0.0</u>	<u>0.0</u>	4.7	3.9
Avg.	0.0	0.0		

The sample submitted, in its original state, **meets** the minimum requirements of the above standard. The char length may not exceed 6.0 inches for any individual specimen and the average afterflame time may not exceed 4.0 seconds in the length or width directions.

Sincerely,

Brian S. Dement

BSD/mr

